





GRADING DESCRIPTIONS


PRIME GRADE

Sample	Allowed	Not allowed
	<ul style="list-style-type: none"> • Knots up to max 15 mm • Cracks up to max 20 mm • Light colour differences 	<ul style="list-style-type: none"> • Sapwood • End cracks • Insect damage • Centre core • Ingrown bark • Grown defects • Mechanical defects


SELECT (RUSTIC A)

Sample	Allowed	Not allowed
	<ul style="list-style-type: none"> • Knots up to max 40 mm • Cracks up to max 20 mm • Natural colour differences • Sapwood up to max 10 mm 	<ul style="list-style-type: none"> • End cracks • Insect damage • Centre core • Ingrown bark • Grown defects • Mechanical defects

RUSTIC MIX

Sample	Allowed	Not allowed
	<ul style="list-style-type: none"> • A mixture of approx. 50% Rustic A and 50 % Rustic B 	<ul style="list-style-type: none"> • A mixture of approx. 50% Rustic A and 50 % Rustic B

RUSTIC B

Sample	Allowed	Not allowed
	<ul style="list-style-type: none"> • Knots up to max 80 mm • Open defects up to max 60 mm • Cracks up to 400 mm • Sapwood up to max 25 mm • Centre core • Grown defects up to max 10 mm • Natural colour differences 	<ul style="list-style-type: none"> • Insect damage • Mechanical defects • Ingrown bark